

HOT JOINT PAINT TECHNICAL DATA SHEET

CHARACTERISTICS

HOT JOINT PAINT

Primarily used for sealing edges of freshly laid tarmac

HOT JOINT PAINT

Black and semi-solid in appearance and supplied in 12.5kg cardboard containers and 20kg plastic buckets

HOT JOINT PAINT

Contents of containers should be removed and put into a bitumen boiler. It is important to ensure that containers and application area is free of water to avoid instant steam formation from molten bitumen

HOT JOINT PAINT

Heat to a recommended temperature of 150_C

Property	Units	Test Method	Specified Limit(s) HOT JOINT
Penetration @ 25_C	dmm	EN 1426	20-30
Softening Point	_C	EN 1427	70-80 minimum
Flash Point (COC)	_C	-	215
Density	-	-	approx. 1



BituChem Building Products
HEAD OFFICE:
Laymore Road
Forest Vale Industrial Estate
Cinderford
Gloucestershire GL14 2YH

Phone:
01594 826768
Fax:
01594 826948
E-mail: info@bituchem.com
Website: www.bituchem.com

BITUCHEM BUILDING PRODUCTS LTD