



BITUCHEM BUILDING PRODUCTS LTD

MANUFACTURERS OF BITUMINOUS PRODUCTS

Laymore Road, Forest Vale Industrial Estate, Cinderford, Gloucestershire, GL14 2YH
Tel: +44 (0) 1594 826768 Fax: +44 (0) 1594 826948
Email: info@bituchem.com Web: http://www.bituchem.com

TECHNICAL DATA SHEET HOT JOINT PAINT

HOT JOINT PAINT

Primarily used for sealing edges of freshly laid tarmac

HOT JOINT PAINT

Black and semi-solid in appearance and supplied in
12.5kg cardboard containers and 20kg plastic buckets

HOT JOINT PAINT

Contents of containers should be removed and put into a
bitumen boiler. It is important to ensure that containers
and application area is free of water to avoid instant
steam formation from molten bitumen

HOT JOINT PAINT

Heat to a recommended temperature of 150°C

Property	Units	Test Method	Specified Limit(s)
HOT JOINT			
Penetration @ 25°C		EN 1426	40-60
Softening Point	°C	EN 1427	40-50 minimum
Flash Point (COC)	°C	-	215
Density	-	-	approx. 1

Issue	1					
Date	08/12/11					
Approved	R. Lord					