



BITUCHEM BUILDING PRODUCTS LTD

MANUFACTURERS OF BITUMINOUS PRODUCTS

Laymore Road, Forest Vale Industrial Estate, Cinderford, Gloucestershire, GL14 2YH
Tel: +44 (0) 1594 826768 Fax: +44 (0) 1594 826948
Email: info@bituchem.com Web: http://www.bituchem.com

TECHNICAL DATA SHEET COLD SEAL PAINT

COLD SEAL PAINT

A general purpose cold applied emulsion for joint painting of vertical joints

COLD SEAL PAINT

Quick drying. Under normal conditions will be dry in 30 minutes

COLD SEAL PAINT

Conforms with the recommendations of the HAUC report. Minimum 70% bitumen content

Complies with MCHW 900 series clause 903 sub clause 22

COLD SEAL PAINT

A damp soft fibre head brush should be used to apply on vertical joints. Alternatively Cold seal paint can be poured out of spouted can.

Property	Units	Test Method	Specified Limit(s)
COLD SEAL			
Penetration @ 25°C	dmm	EN 1426	50-70
Softening Point	°C	EN 1427	50 minimum
Ductility Recovery @ 25°C (minimum)	%	EN 13398	20-30

Issue	1					
Date	08/12/11					
Approved	R. Lord					