

COLD SEAL PAINT TECHNICAL DATA SHEET

CHARACTERISTICS

COLD SEAL PAINT

A general purpose cold applied emulsion for joint painting of vertical joints

COLD SEAL PAINT

Quick drying. Under normal conditions will be dry in 30 minutes

COLD SEAL PAINT

conforms with the recommendations of the Hauc report. Minimum 70% bitumen content
complies with MCHW 900 series clause 903 sub clause 22

COLD SEAL PAINT

A damp soft fibre head brush should be used to apply on vertical joints. Alternatively Cold seal paint can be poured out of spouted can.

Property	Units	Test Method	Specified Limit(s) COLD SEAL
Penetration @ 25_C	dmm	EN 1426	50-70
Softening Point	_C	EN 1427	50 minimum
Ductility Recovery @ 25_C (minimum)	%	prEN 13398 (modified)	20-30
Storage Stability @ 160_C for 7 days	-	Specification for Highway Works	5_C Maximum



BituChem Building Products
HEAD OFFICE:
Laymore Road
Forest Vale Industrial Estate
Cinderford
Gloucestershire GL14 2YH

Phone:
01594 826768
Fax:
01594 826948
E-mail: info@bituchem.com
Website: www.bituchem.com

BITUCHEM BUILDING PRODUCTS LTD