

K1-40 TECHNICAL DATA SHEET

CHARACTERISTICS

K140

A cationic 40% bitumen emulsion produced to EN13808

K140

Can be provided in bulk, 200kg drums or 25kg containers

K140

Is to be used as a bond between different asphalt layers, concrete curing, grass growing

K140

Rates of spread guidelines are given in BS4987 and BS594

Property	Units	Test Method	Specified Limit(s) K140
Penetration @ 25_C	dmm	EN 1426	160-220
Softening Point	_C	EN 1427	37 minimum
Ductility Recovery @ 25_C (minimum)	%	prEN 13398 (modified)	20-30
Storage Stability @ 160_C for 7 days	-	Specification for Highway Works	5_C Maximum



BituChem Building Products
HEAD OFFICE:
Laymore Road
Forest Vale Industrial Estate
Cinderford
Gloucestershire GL14 2YH

Phone:
01594 826768
Fax:
01594 826948
E-mail: info@bituchem.com

BITUCHEM BUILDING PRODUCTS LTD