



BITUCHEM BUILDING PRODUCTS LTD

MANUFACTURERS OF BITUMINOUS PRODUCTS

Laymore Road, Forest Vale Industrial Estate, Cinderford, Gloucestershire, GL14 2YH
Tel: +44 (0) 1594 826768 Fax: +44 (0) 1594 826948
Email: info@bituchem.com Web: http://www.bituchem.com

TECHNICAL DATA SHEET K140

CHARACTERISTICS

K140

A cationic bitumen emulsion to EN13808 C40B4

K140

Can be provided in bulk, 200kg drums or 25kg containers

K140

Is to be used as a bond between different asphalt layers,
concrete curing, grass growing

K140

Rates of spread guidelines are given in BS EN 594987

Requirement	Selected classes from Table 3
Perceptible properties	NPD – Class 0
Particle polarity	Positive – Class 2
Breaking Value	70 – 130 – Class 4
Mixing stability with cement	NPD – Class 0
Fines mixing time	NPD – Class 0
Penetration power	NPD – Class 0
Binder content (by water content)	38 – 42 Class 2
Recovered binder content (by distillation)	≥ 38 Class 2
Oil distillate content	≤ 2.0 Class 2
Efflux time 2mm at 40 ° C	NPD – Class 0
Dynamic viscosity at 40 ° C	NPD – Class 0
Residue on sieving	≤ 0.1- 0.5mm Sieve Class 2 ≤ 0.5 – 0.16mm Sieve Class 3
Residue on sieving (seven days storage)	NPD – Class 0
Setting tendency	≤ 5 Class 2
Adhesivity	NPD – Class 0

Issue	1					
Date	08/12/11					
Approved	R. Lord					



BITUCHEM BUILDING PRODUCTS LTD

MANUFACTURERS OF BITUMINOUS PRODUCTS

Laymore Road, Forest Vale Industrial Estate, Cinderford, Gloucestershire, GL14 2YH
Tel: +44 (0) 1594 826768 Fax: +44 (0) 1594 826948
Email: info@bituchem.com Web: http://www.bituchem.com

TECHNICAL DATA SHEET K140

Requirement	Selected classes from Table 4 (following evaporation)	Selected classes from Table 5 (following evaporation, stabilisation and aging)
Penetration	≤ 220 Class 5	NPD – Class 0
Softening point	≥ 35 Class 6	NPD – Class 0
Efflux time (10mm cup at 40 °C)	NPD – Class 0	NPD – Class 0
Dynamic viscosity at 60 °C	NPD – Class 0	NPD – Class 0
Kinematic viscosity at 60 °C	NPD – Class 0	NPD – Class 0
Cohesion energy by tensile test	NPD – Class 0	NPD – Class 0
Cohesion energy by force ductility at 10 °C	NPD – Class 0	NPD – Class 0
Cohesion energy by force ductility at 25 °C	NPD – Class 0	NPD – Class 0
Cohesion by pendulum test	NPD – Class 0	NPD – Class 0
Elastic recovery at 10 °C	NPD – Class 0	NPD – Class 0
Elastic recovery at 25 °C	TBR – Class 1	NPD – Class 0

Issue	1					
Date	08/12/11					
Approved	R. Lord					