

# K1-60 TECHNICAL DATA SHEET

## CHARACTERISTICS

### K160

A cationic emulsion produced to EN13808

### K160

Can be provided in bulk, 200kg drums or 25kg containers

### K160

Is to be used as a bond between different asphalt layers,  
Surface dressing, or patching

### K160

Rates of spread guidelines are given in BS4987 and BS594  
and roadnote 39

Property	Units	Test Method	Specified Limit(s) K140
Penetration @ 25_C	dmm	EN 1426	160-220
Softening Point	_C	EN 1427	37 minimum
Ductility Recovery @ 25_C (minimum)	%	prEN 13398 (modified)	20-30
Storage Stability @ 160_C for 7 days	-	Specification for Highway Works	5_C Maximum



BituChem Building Products  
HEAD OFFICE:  
Laymore Road  
Forest Vale Industrial Estate  
Cinderford  
Gloucestershire GL14 2YH

Phone:  
01594 826768  
Fax:  
01594 826948  
E-mail: [info@bituchem.com](mailto:info@bituchem.com)  
Website: [www.bituchem.com](http://www.bituchem.com)

## BITUCHEM BUILDING PRODUCTS LTD